## Nanostructured Ancient Damascus Blades

Pätzke, Nora<sup>1</sup> Levin, Alexandr A.<sup>1</sup> Shakhverdova, Irina P.<sup>1</sup> Reibold, Marianne<sup>1</sup> Kochmann, Werner<sup>2</sup> Paufler, Peter<sup>1</sup> Meyer, Dirk C.<sup>1</sup>

<sup>1</sup>Institut f.Strukturphysik, TU Dresden, D-01062 Dresden <sup>2</sup>Krüllsstr.4b, D-06766 Wolfen

Legends tell how Damascene blades exhibiting extraordinary mechanical and optical properties had been manufactured following secret recipes (Validi (1936), Panseri (1965), Piaskowski (1978)). During the last decades more sophisticated metallurgical methods have revealed details of the microstructure of this crucible (or wootz) steel. There are indications that impurities and unconventional thermo-mechanical treatments might have an essential influence on the typical Damast pattern (Sherby (1995), Verhoeven (1998)). Using scanning and high-resolution transmission electron microscopy, X-ray diffraction as well as micro- and nanohardness measurements we have analysed specimens of two genuine Damascus sabres, which date back to the 17<sup>th</sup> century. They were kindly left to us by the Historic Museum Berne. Significant new details of the microstructure that have been revealed during our study are nanowires of cementite Fe<sub>3</sub>C (Kochmann (2004), Levin (2005)) as well as carbon nanotubes (Reibold (2006)) and present work). Moreover, using X-ray diffraction,  $Fe_7C_3$  has been detected which is known as catalyst for hydrocarbon synthesis and which eventually converts to Fe<sub>3</sub>C (Herbstein (1964)). Since carbon nanotubes have become known as forming catalytically from natural fibres (Goodell (2007)), this sheds a new light on early reports on the addition of organic material (wood, leaves) into the crucible, which was used by Indian metallurgists (Schwarz (1901)). Hence, we speculate that there is a connection between transition metal impurities, hydrocarbons, nanotubes, nanowires and cementite pattern. Moreover, the existence of ordered cementite wires at nanoscale should have consequences for the mechanical properties. In addition to the nanoindentation measurements mentioned above, we have performed nanoscratch tests to characterise the striking stability of the cutting edge more quantitatively.

References

Goodell B, XieX, QianY, Zhang D, Peterson M, Jellison J (2007) Method of producing carbon nanotubes using natural fiber as the starting substrate. USPTO Serial No. 60/898, 884. Febr.1,2007

Herbstein F H , Snyman J A (1964) Identification of Eckstrom-Adcock Iron Carbide as Fe<sub>7</sub>C<sub>3</sub>. Inorg.Chem. 3, 894-896

Levin A A, Meyer D C, Reibold M, Kochmann W, Pätzke N, Paufler P(2005)Microstructure of a genuine Damascus sabre. Crystal Res. Technol. 40,905-916

Panseri C (1965) Damascus steel in legend and reality. Gladius ,4, 5-66

Piaskowski J (1978) Damascus steel: The greatest achievement of early metallurgy. Abhat an-Nadwa al-Alamiya li-Tarih al-Ulum inda 'l-Arab 1(2),238-245

Reibold M, Paufler P, Levin A A, Kochmann W, Pätzke N, Meyer D C(2006) Carbon nanotubes in an ancient Damascus sabre. Nature 444, 286

Schwarz C Ritter v (1901) Ueber die Eisen- und Stahlindustrie Ostindiens. Stahl u.Eisen 21, 209-211

Sherby O (1995) Damascus steel and superplasticity I. SAMPE Journ. 31, 10-17

Verhoeven J D , Pendray A H , Dauksch W E (1998) The key role of impurities in ancient Damascus steel blades. JOM 50, 58-64

Abs. No. 208 Meeting: DMG 2008 submitted by: Paufler, Peter email: paufler@physik.tudresden.de date: 0000-00-00 Req. presentation: Poster Req. session: S17